

# Primary Lithium Battery CR15270

3.0V [Li-MnO<sub>2</sub>] CR2-size spiral cell



#### **BENEFITS**

- High Voltage Response, Stable During Most of the Lifetime of the Application
- Energy Density up to 830Wh/L
- Wide Operating Temperature Range (-40 °C ~+85 °C)
- Low Self-discharge Rate (less than 1% per year after 1 year of storage at +25 °C)

### **References Data**

**Nominal capacity** 

#### **Electrical characteristics**

#### Open circuit voltage (at 23±2°C)

≥3.10V

800mAh

1500mA

#### **KEY FEATURES**

- Optimized Battery Structure, Full Discharge Capacity
- Long Endurance
- No Passivation
- GB 8897.4-2008、 IEC 60086.4:2014 and RoHS

#### **MAIN APPLICATIONS**

- Security System
- Smart Metering
- RFID and Tracking System
- Wireless Transmitting
- Smart Home Devices
- Military Devices

# voltage reaches cut-off voltage 2.0V. The capacity can vary at different temperature, discharge current or cut-off voltage.) / Maximum continuous current 800mA

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity.)

(At +25°C, battery discharged at continuous current 1mA until

#### Maximum pulse discharge current

(At +25°C, 2.0V cut-off, battery discharged for minimum 50% of rated capacity with max pulse for 3 seconds after 27 seconds break. The discharged capacity may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult HCB.)

#### Storage (recommended)

**Operating temperature range** 

(For more severe conditions. Consult HCB) **<75%RH** 

### -40°C~+85°C

≤+30°C

(Operation above ambient Temperaure may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult HCB.)

#### HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China P.O.: 430040 Tel: +86(0)27 83248452 Fax: +86(0)27 83248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V2.0 2018 02]

#### HCB BATTERY CO., LTD

Add: Special No 1. Taizhong Avenue, Gaoqiao Industrial Park, Wujiashan Economic Development Zone, Wuhan, P.R.China

P.O.: 430040 Tel: +86(0)27 83248452 Fax: +86(0)27 83248455 Email: haocheng@cnhcb.com Web: www.cnhcb.com No.: HCB-MKT.PM-S[V2.0 2018 02]

# **Primary Lithium Battery CR15270**

3.0V [Li-MnO<sub>2</sub>] **CR2-size spiral cell** 

Physical characteristics	
15.0±0.2mm	
27.5±0.5mm	
13.0g	
0.30g	

MSDS as per request Diode (1N4007, 1N5819) PTC (SRS175...) Tag, wire, connector, etc. available

## $\Phi 6.2 \pm 0.1$ ഹ $5\pm 0.$ 27. $\Phi 15.0 \pm 0.2$

Dimensions in mm (GB1804-m)

Do Not Dismantle

Do Not Incinerate

• Do Not Mix New and Used Batteries

Do Not Heat Above 100°C


### WARNING:

- Do Not Short Circuit
- Do Not Recharge
- Do Not Puncture
- Do Not Crush

Voltage (V) 2.6 2.4 2.2 2.0 -60 -40 -20

3.4 3.2 3.0

2.8



20

Temperature (°C)

40

60

2.Typical discharge profiles with different temperature (at discharge stable phase)


1 mA

1 00mA

8 00mA

80

100



1.Typical discharge profiles at 23±2°C (at mid-discharge)

